取向电工钢

Cold Rolled Grain-oriented Electrical Steel

佛山市全世麦克磁材有限公司

TRANSMART INDUSTRIAL LIMITED

首钢取向电工钢技术指标　　Technical Indexes

产品规格　　Product Specification

公称厚度 Nominal Thickness (mm)	公称宽度 Nominal Width (mm)	内径 Inside Diameter (mm)	重量 Weight (t)
0.20、0.23、0.27、0.30	800～1200	508	2～5

尺寸公差　　Dimensional Tolerances

公称厚度 Nominal Thickness (mm)	厚度偏差 Thickness Tolerance (mm)	横向厚差 Transverse Thickness Tolerance (mm)	纵向厚差 Longitudinal Thickness Tolerance (mm)	宽度偏差 Width Tolerance (mm)	不平度 Flatness (%)	镰刀弯 Camber 2m (mm)
0.20	±0.020	≤0.015	≤0.020	0～+1.0	≤1.0	≤0.8
0.23						
0.27						
0.30						

注：（1）横向厚差是指边部 15mm 以内，垂直于轧制方向上的厚度偏差。

（2）纵向厚差是平行于轧制方向上任意 2m 长度钢带上的厚度偏差。

（3）对于有特殊要求的用户，可以特殊定制。

Note: (1) Traverse thickness deviation refers to the thickness difference between the sheet center and 15mm from the edge.

(2) The longitudinal thickness difference is the difference of the measured maximum thickness and the minimum thickness in the longitudinal direction at an arbitrary 2m length of steel on an arbitrary coil.

(3) Please consult us if you have special dimensional requirements.

首钢取向电工钢技术指标　　Technical Indexes


电磁性能标准值　Standard Electromagnetic Properties


类型 Type	公称厚度 Nominal Thickness (mm)	牌号 Grade	理论密度 Density (kg/dm^3)	比总损耗 $P_{17/50}$ Core Loss (W/kg)	磁极化强度 B_8 Magnetic Induction (T)
高磁感型 High Magnetic Induction Type	0.20	20SQG080	7.65	0.80	1.89
		20SQG085	7.65	0.85	1.89
	0.23	23SQG085	7.65	0.85	1.89
		23SQG090	7.65	0.90	1.89
		23SQG095	7.65	0.95	1.89
	0.27	27SQG090	7.65	0.90	1.89
		27SQG095	7.65	0.95	1.89
		27SQG100	7.65	1.00	1.89
	0.30	30SQG100	7.65	1.00	1.89
		30SQG105	7.65	1.05	1.89
		30SQG120	7.65	1.20	1.89
细化磁畴高磁感型 Domain Refined High Magnetic Induction Type	0.20	20SQGD070	7.65	0.70	1.89
		20SQGD075	7.65	0.75	1.89
	0.23	23SQGD075	7.65	0.75	1.89
		23SQGD080	7.65	0.80	1.89
		23SQGD085	7.65	0.85	1.89
	0.27	27SQGD085	7.65	0.85	1.89
		27SQGD090	7.65	0.90	1.89
		27SQGD095	7.65	0.95	1.89
	0.30	30SQGD095	7.65	0.95	1.89
		30SQGD100	7.65	1.00	1.89


首钢取向电工钢技术指标　　Technical Indexes


电磁性能典型值　Typical Electromagnetic Properties


类型 Type	公称厚度 Nominal Thickness (mm)	牌号 Grade	理论密度 Density (kg/dm^3)	比总损耗 $P_{17/50}$ Core Loss (W/kg)	磁极化强度 B_8 Magnetic Induction (T)
高磁感型 High Magnetic Induction Type	0.20	20SQG080	7.65	0.79	1.91
		20SQG085	7.65	0.83	1.90
	0.23	23SQG085	7.65	0.83	1.91
		23SQG090	7.65	0.86	1.91
		23SQG095	7.65	0.90	1.90
	0.27	27SQG090	7.65	0.88	1.91
		27SQG095	7.65	0.90	1.91
		27SQG100	7.65	0.95	1.91
	0.30	30SQG100	7.65	0.97	1.91
		30SQG105	7.65	1.00	1.91
		30SQG120	7.65	1.05	1.91
细化磁畴高磁感型 Domain Refined High Magnetic Induction Type	0.20	20SQGD070	7.65	0.68	1.91
		20SQGD075	7.65	0.73	1.90
	0.23	23SQGD075	7.65	0.73	1.91
		23SQGD080	7.65	0.76	1.91
		23SQGD085	7.65	0.80	1.90
	0.27	27SQGD085	7.65	0.83	1.91
		27SQGD090	7.65	0.85	1.91
		27SQGD095	7.65	0.90	1.91
	0.30	30SQGD095	7.65	0.93	1.91
		30SQGD100	7.65	0.95	1.91



铁损曲线
Core loss curves
20SQG080
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
20SQG080
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
20SQG080
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



铁损曲线
Core loss curves
20SQG085
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
20SQG085
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
20SQG085
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



铁损曲线
Core loss curves
23SQG085
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
23SQG085
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
23SQG085
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



有效磁场曲线
Exciting force Curve
23SQG085
试样：30×300 mm
测试：爱波斯坦方圈
Sample: 30×300 mm
Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
23SQG090
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
23SQG090
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
23SQG090
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



有效磁场曲线
Exciting force Curve
23SQG090
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
27SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
27SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



有效磁场曲线
Exciting force Curve
27SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
30SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
30SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
30SQG100
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



有效磁场曲线
Exciting force Curve
30SQG100
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
30SQG105
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
30SQG105
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
30SQG105
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



有效磁场曲线
Exciting force Curve
30SQG105
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
30SQG120
试样：30×300 mm
测试：爱波斯坦方圈
Sample: 30×300 mm
Test: Epstein test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
30SQG120
试样：30×300 mm
Sample: 30×300 mm
测试：爱波斯坦方圈
Test: Epstein test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
30SQG120
试样：30×300 mm
Sample: 30×300 mm
测试：爱泼斯坦方圈
Test: Epstein test



有效磁场曲线
Exciting force Curve
30SQG120
试样：30×300 mm Sample: 30×300 mm
测试：爱波斯坦方圈 Test: Epstein test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
20SQGD070
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
20SQGD070
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
20SQGD070
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



铁损曲线
Core loss curves
20SQGD075
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
20SQGD075
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
20SQGD075
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
20SQGD075
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)
2.1
2.0
1.9
1.8
1.7
1.6
1.5
1.4
1.3
1.2
1.1
1.0
0.9
0.8
0.7
0.6
0.5
0.4
0.3
0.2
1
2
3
4
5
6
7
8
9
10
20
50
100
200
500
1000
2000
3000
4000
5000
6000
7000
8000
9000
10000



铁损曲线
Core loss curves
23SQGD075
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
23SQGD075
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
23SQGD075
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



铁损曲线
Core loss curves
23SQGD080
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
23SQGD080
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
23SQGD080
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
23SQGD080
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)
2.1
2.0
1.9
1.8
1.7
1.6
1.5
1.4
1.3
1.2
1.1
1.0
0.9
0.8
0.7
0.6
0.5
0.4
0.3
0.2
1
2
3
4
5
6
7
8
9
10
20
50
100
200
500
1000
3000
5000
10000



铁损曲线
Core loss curves
23SQGD085
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
23SQGD085
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
23SQGD085
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
23SQGD085
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
27SQGD085
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
27SQGD085
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
27SQGD085
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
27SQGD085
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
27SQGD090
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
27SQGD090
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
27SQGD090
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
27SQGD090
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
27SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
27SQGD095
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
27SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test



有效磁场曲线
Exciting force Curve
27SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)



铁损曲线
Core loss curves
30SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)



激磁功率曲线
Exciting power curves
30SQGD095
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)



磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
30SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test


有效磁场曲线
Exciting force Curve
30SQGD095
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)


铁损曲线
Core loss curves
30SQGD100
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
60Hz
磁感 Magnetic flux density (T)
铁损 Core loss (W/kg)


激磁功率曲线
Exciting power curves
30SQGD100
试样：500×500 mm Sample: 500×500 mm
测试：单片检测 Test: single sheet test
60Hz
50Hz
磁感 Magnetic flux density (T)
激磁功率 Exciting power (VA/kg)


磁导率 Permeability μ (mH/m)
磁感 Magnetic flux density B (T)
磁场强度 Magnetizing force H (A/m)
B-H
H-μ
直流磁化曲线
直流磁导率曲线
D.C. magnetization curve
D.C. permeability curve
30SQGD100
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test


有效磁场曲线
Exciting force Curve
30SQGD100
试样：500×500 mm
测试：单片检测
Sample: 500×500 mm
Test: single sheet test
50Hz
磁感 Magnetic flux density (T)
有效磁场 Exciting force (A/m)

佛山市全世麦克磁材有限公司 TRANSMART INDUSTRIAL LIMITED
Tel : +86 757 8622 8688 | Email : sales@transmart.net | Website : www.transmart.net