



Amorphous Block Core

Electromagnetic Characteristic

Saturation Flux Density B_s	1.56T (Ref.)
Saturation magnetstriction λ_s	27ppm
Core Lose P_{cm}	2.3 W/kg (Ref.) at 10 kHz, 0.1T
Curie temperature T_c	392 deg.C (Ref.)
Maximum operation temperature	130 deg.C

